

CoreLite[®] Board

Product Data Sheet

Last Revised: October 05, 2015

CoreLite[®] Board is a cost-effective closed-cell PVC foam specially formulated to provide high physical properties and be recyclable. Engineered for easy workability, weatherproof and insulation properties, and excellent fire behavior. It is characterized for its phenomenal screw retention and amazing resistance to moisture; it will not rot, mold or mildew. It is also compatible with multiple resins and adhesives.

CoreLite[®] Board is a stand-alone product and can be used without skins as a replacements for wood and plywood. This PVC foam has excellent fastener pullout strength and high flexural strength and stiffness. CoreLite[®] Board is 27% lighter than plywood.

PROCESSING

- Adhesive bonding
- Prepreg processing (up to 180°C or 355°F)
- Contact Molding (hand/spray)
- Compression molding (GMT, SMC)
- Resin infusion / injection (VARTM / RTM)



APPLICATIONS

Marine: Transom Boards, Consoles, Seat Bottoms, Decks, Floors, Bulkheads, Stringers, Superstructures, Engine Beds, Interiors, Local Reinforcements, Tooling and Molds

Transportation: Primary Body Structure, Interior Panels, Sidewalls, Floors, Roofs and Engine Covers

Construction: Decks, Roof Panels, Doors, Windows, Cabinets, Tables and Architectural Panels

Industrial: Covers, Containers, Refrigeration, Tanks, Local Reinforcements, Sporting goods, Tooling and Molds

Signs: Outdoor Displays, Dimensional Lettering, Dimensional Signs and Channel Letter Backer

CoreLite[®] Board

MECHANICAL PROPERTIES - Metric		
TEST STANDARDS	UNITS	VALUES
Density per ASTM C271	Kg. / M3	448,52
Compressive Strength per ASTM D1621	MPa	5,84
Compressive Modulus per ASTM D1621-B	MPa	2,92
Tensile Strength per ASTM C297	MPa	3,32
Shear Strength per ASTM C273	MPa	3,07
Shear Modulus per ASTM C273	MPa	38,05
Flexural Strength per ASTM D790	MPa	12,40
Peel Strength per ASTM D1062	MPa	11,76
Screw Torque	N·m	2,28
Screw Pull	Kg.	102,60
Standard Sheet dimensions	mm	1.220 x 2.440
Thickness	mm	9,53 to 50,80

Values shown are nominal average determined from independent laboratory and house testing. Tests are parallel to the plane.

Processing temperature:	< 94 °C
Water Absorption:	< 1%
Percent Elongation at max load:	1,404%
Density Tolerance:	+ / - 10%
Color:	White

Disclaimer: The information and data presented herein are subject to revision. CoreLite Inc. reserves the right to release replacement data. The data presented is derived from in house and independent testing. Calculations should be verified with physical test. The data is provided without liability to CoreLite, Inc. or its agents and does not constitute warranty or representation in respect to the material or its use.