



FIX15 - MSP15

SOLAS Certified MED 0327QA,
U.S. Coast Guard Approved No.
164.106/1121/WCL

Revision: 01/2011

Page 1 of 2

Technical Data:

Base	MS Polymer®
Consistency, Density	Stable Paste, 1.55kg/m ³
Curing system	Moisture Cure
Skin Formation(*)	Approx. 15 min (23°C/ 50% R.H)
Tack Free Time (*)	Approx. 4 hours (23°C/ 50% R.H)
Cure Rate (*)	3mm/24hr (23°C/50%R.H)
Hardness	48 Shore A
Change In Volume	<2%
Specific Gravity	1.55 kg/m ³
Maximum Deformation	± 20%
Temperature Resistance (cured)	-40°C→100°C
Elastic Modulus 100%	1.1 N/mm ² (ISO37, DIN 53504)
Tensile Strength	2.2 N/mm ² (ISO37, DIN 53504)
Elongation At Break	> 300% (ISO37, DIN53504)
Shear Strength	>1.6N/mm ² (ISO37, DIN 53504)

(*) Values may vary depending on environmental conditions

Product:

Fixseal MSP15 is a high quality single component joint sealant with high adhesive strength. It is based on MS Polymer®, which is chemically neutral and fully elastic with excellent primerless bonding. For use in low movement joints, adhesion and waterproofing in the construction, automotive, marine and aerospace industries where a strong bond and/or UV resistant flexible seal is required. Suitable for below waterline applications.

Characteristics:

- High bond strength on a wide variety of substrates
- Non Yellowing white, and colourfast black
- High performance mechanical properties
- Flexible elastic rubber; movement accommodation up to 20%
- Assed under criteria of NOHSC Australia and

considered as non-toxic, Certificate No.2146.

- No bubble formation within the sealant
- Primerless adhesion (except where capillary water pressure can occur)
- Easy to tool and finish
- Excellent extrudability and UV resistance
- Ecological advantages- free from isocyanates, solvents, halogens and acids
- Minimal health and safety considerations
- Can be wet on wet painted with all water based paints and many other systems*
- No staining of porous materials such as natural stone, granite, marble, etc.

Applications:

Sealing and bonding of areas with high traffic, floor joints and low movement wall joints. Suitable for bonding and sealing but not limited to

Note: The contents contained in this documentation are the result of our experiments and our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the real number of possible applications which are out of our control we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments and compatibility tests.

Fixtech Pty Ltd. PO Box 568, Southport, Qld 4215. Tel: +61 (0)7 5530 1099. Fax: +61 (0)7 5530 1322

Email: info@fixtech.com.au

Web: www.fixtech.com.au



FIX15 - MSP15

Revision: 01/2011

Page 2 of 2

Applications (cont.):

steel, aluminium, stainless, PVC, fiberglass, concrete, composite, glass, timber, mirrors, polystyrene, rubber, PU foam, etc.... Connection joints in sheet metal fabrication. Sealing and bonding of coachwork, caravans, boats, commercial ferries and ships, buses, aircraft, domestic and commercial construction.

Packaging:

Colour - Black and White

Packaging – 290mL cartridge, 600mL foil bag

Shelf life:

15 months Cartridges; 15 months Foil Bags

In unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°.

Surfaces:

Typical Surface: Abraded with red abrasive pad or suitable sand paper, clean, dry, free of dust and grease, wipe surface clean with Industrial Alcohol.

Glass: clean, dry, free of dust and grease, wipe surface clean with Industrial Alcohol.

Priming:

a): For porous substrates we recommend Primer PR10 be applied.

b): PE or PP Plastics we recommend Primer PR20 be applied for good adhesion.

Joint Dimension:

Minimal Width: 2mm (bonding)
5mm (joint)

Maximum Width: 10mm (bonding)
30mm (joint)

Minimum Depth: 5mm(joint)

Recommendation: Width of joint = 2 x depth

Application:

Method: Manual or pneumatic caulking gun

Application temperature: +5°C to +35°C

Clean up: Methylated Spirits or industrial alcohol cleaner immediately after application and before curing

Tooling: mild diluted soapy solution (e.g. pH neutral dishwashing liquid diluted in fresh clean water), before skin formation

Repair: Fixseal FIX15 - MSP15

Health- and Safety Recommendation:

Apply the usual industrial hygiene. Wear gloves . Safety Glasses.

Remarks:

- Fixseal MSP15 may be overpainted with water based paints, however due to the large number of paintes such as and not limited to 1 and 2 pack PU paints, acrylics, 2 pack varnishes that are available we strongly recommend compatability tests before application.
- The drying time of some alkyd paint systems may increase and some enamel and oil based paints will not cure properly.
- Fixseal MSP15 can be applied to a wide variety of substrates. Due to the fact that the specific properties of substrates will differ from manufacturer to manufacturer we strongly recommend compatibility tests.

Note: The contents contained in this documentation are the result of our experiments and our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the real number of possible applications which are out of our control we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments and compatibility tests.

Fixtech Pty Ltd. PO Box 568, Southport, Qld 4215. Tel: +61 (0)7 5530 1099. Fax: +61 (0)7 5530 1322

Email: info@fixtech.com.au

Web: www.fixtech.com.au